



Laybond Wood

HIGH STRENGTH ADHESIVE FOR SURFACE BONDING WOOD FLOORING

Date: 11 December 2015

Fact Sheet No.: TDS00893

YOUR SMART ADVANTAGES

- Synthetic polymer solvented adhesive
- Suitable for all types of wood flooring
- High bond strength

USES

Bostik Laybond Wood is a filled solution of synthetic polymer resins in a blend of solvents which is formulated to a trowelling consistency.

Bostik Laybond Wood is ideal for bonding all types of parquet flooring, woodblock and woodstrip to strong subfloors including concrete, cementitious screeds, flooring grade plywood, chipboard, hardboard, and smoothing compounds. It is of particular use where the nature of the wood flooring makes it particularly prone to warping when bonded with waterborne adhesives.

Bostik Laybond Wood is suitable for use with warm water underfloor heating installations (surface temperature must not exceed 27°C). Heating systems must be switched off for 48 hours before and after installation.

PRODUCT CHARACTERISTICS

| | | |
|------------------|--------------------------------|------|
| Colour | Off White | |
| Form | High viscosity paste | |
| Composition | Solvent blend polymer & resins | |
| Type of Solvent | Industrial methylated spirits | |
| Specific Gravity | 1.5 approx. | |
| Product Codes | 30811816 | 15kg |
| | 30814553 | 7kg |

Storage/Shelf Life

Store for up to 12 months from date of manufacture when stored in original, unopened packaging within the temperature range of +5°C to +40°C and out of direct sunlight. Protect from frost. Product must be stored under the conditions that meet the requirements of the Highly Flammable Liquids and Liquefied Petroleum Gases Regulations (1972).

TYPICAL PERFORMANCE DATA (approx.)

| | |
|-------------------------|--|
| Application Temperature | +5°C to +30°C |
| Service Temperature | Up to 35°C |
| Open Time | 10 to 15 minutes |
| Flashpoint | 17°C |
| Coverage | Woodstrip/Woodplank: using a 2.7mm x 5mm notched trowel, coverage is 16m ² per 15kg, 7.5m ² per 7kg. Woodblock/Parquet Panels: using a 2mm x 6mm notched trowel, coverage is 25m ² per 15kg, 11.5m ² per 7kg. |

DIRECTIONS FOR USE

IMPORTANT: Before using Bostik Laybond Wood refer to the relevant Health & Safety Data Sheet, available at www.bostik.co.uk.

All phases of installation should comply with the latest editions of the following standards:

BS 8102 Code of Practice for protection of building against water from the ground.

BS 8201 Code of Practice for Flooring of timber, timber products and wood based panel products.



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk

Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

PREPARATION

Subfloor:

1. Ensure the subfloor is clean, sound, dry and free from contaminants that may hinder adhesion.
2. The subfloor should be tested in accordance with British Standards using a properly calibrated and insulated hygrometer.
3. A reading of 75% RH or less confirms that the subfloor is satisfactorily dry. Where this has not been attained it is necessary to apply a Bostik Screedmaster surface membrane to suppress residual moisture. For further information contact Flooring Technical Services Department.
4. Underfloor heating systems must be switched off for 48 hours before and after installation.

Smoothing Compounds:

5. Mechanically remove any surface treatments on concrete bases.
6. Repair any deep indentations in the subfloor with Bostik Screedmaster Rapid Repair Mortar and apply a suitable Bostik Screedmaster smoothing compound at a minimum thickness of 3mm.

Existing Floor Coverings:

7. Not recommended for use over existing floor coverings.

PRIMING

8. Surfaces should be thoroughly cleaned and vacuumed. Prime boards and other porous surfaces with diluted Screedmaster Universal Primer (dilute 2 parts water to 1 part Screedmaster Universal Primer) and allow to dry. This is particularly important with hardboard, chipboard and plywood. Ensure that the floor covering manufacturer recommends the floor covering for use with the particular substrate.

APPLICATION

Porous Surfaces:

9. Spread evenly over the floor surface with a triangular notched trowel. Wood Block and Wood Mosaic Panels use a 2mm deep x 6mm trowel. Wood Plank or Woodstrip a minimum B2, 2.7mm deep x 5mm trowel. Uneven floor or wood with a profile use B3, 3mm x 6mm trowel.
10. Ensure a good overall contact is achieved between wood and substrate.
11. Spread the adhesive with a sweeping motion at a 60° angle.
12. Place the wood into the adhesive whilst it is still wet. Only apply enough to work within 10 to 15 minutes, usually 1m².
13. Place wood in the adhesive, and press firmly to ensure good overall contact.
14. The bonded wood should then be left a minimum of 24 hours before sanding and trafficking take place.

Non/Low-Porous Surfaces:

15. Apply a suitable Bostik Screedmaster smoothing compound to a minimum depth of 3mm and allow to dry overnight. Proceed as for Porous Surfaces.

CLEANING

16. Do not allow to dry. Clean tools with methylated spirits immediately after use. Remove any adhesive from the surface of the floor covering with a cloth dampened with methylated spirits (test for colour fastness on small trial area).

PRECAUTIONS IN USE

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.co.uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik Laybond Wood, available at www.bostik.co.uk.

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk

Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

| | | | |
|---|--------------------|-------------------|--|
| Sales | Tel: 0844 371 1192 | Fax: 01785 241818 | customer.service@bostik.com |
| Technical Advice | Tel: 0844 371 1197 | Fax: 01785 272867 | technical.service@bostik.com |
| Technical Data & COSHH (MSDS) Data Sheets | Tel: 01785 272625 | Fax: 01785 212962 | stafford.gatehouse@bostik.com |



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk
Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.