

Technical Details And Specification

Floorwise Duet

Construction Recycled Jute Fibres & Other Fibres
Needed to A Strong Polypropylene Scrim;
Backed With Regranulated Rubber Crumb.

Fibre Composition 100% Natural Jute Fibres.

Rubber Composition Regranulated Vehicle Tyres.

Specified Weight 2000 gsm. +/- 5%

Nominal Thickness 11mm. +/- 1mm

Tensile Strength 160 Newtons. Extension at 40N, 3%. ~ pass *
(BS 2576)

Static Loading Thickness Loss of 29% ~ within tolerance *
(BS 4939)

Dynamic Loading Thickness Loss of 27% ~ within tolerance *
(BS 4052)

Retained Work Of Compression 70% ~ within tolerance *
(BS 4098)

Thermal Conductivity Between 2 and 3 togs (resistance factor).

Flammability Low radius of effects of ignition (BS 4790) ~ pass.
M3 (French Epiradiateur)

Suitability Heavy Contract Underlay *

* These test results relate directly to BS5808:1991 ~ Underlays For Textile Floorcoverings.
The data details provided are typical results from independent and internal evaluations.

