







high performance underlay







Specification (Typical Values)		
Yellow Polymer Film with stabilising Mesh Grid		
Ultra High Density Recycled Industrial Foam	+5% -0%	
9mm	±5%	
25.2 Kg	-5%+10%	
11m x 1.37m = 15.07m ²	Width ±2cm Length +15cm	
	Yellow Polymer Film with stabilising Mesh G Ultra High Density Recycled Industrial Foam 9mm 25.2 Kg	

BS5808 1991 (2005) Standards for Carpet Underlay			
Loss in Thickness after Static Loading	BS4939	<5%	
Loss in Thickness after Dynamic Loading	BS4052	<5%	
Work of Compression After Dynamic Loading	BS4098	>140J/m ²	
Retention of Work of Compression	BS4098	>90%	
Flammability – Hot Metal Nut Test	BS4749	Low Radius of Effects	
End Use Classification	BS5808	L/U Luxury Use (Domestic & Commercial Installations)	
Floorwise Reference: F9TR/2/May 2017			
Thermal Resistance	BS4745	2.44 Togs	
Impact Sound Improvement	ISO 140-8	Δ LW 39 dB	







